

# Accelerator CF31

Metal complex

Accelerator CF31 is a cobalt-free accelerator for curing thermoset resins.

CAS number  
proprietary

## Specifications

Appearance	Clear green liquid
Iron	240-300 mg/kg

## Applications

Accelerator CF31 can be used in combination with Butanox M-50 and most other peroxides, such as Trigonox 44B, Butanox LPT and Trigonox K-90 in ambient and elevated temperature curing for most commonly used UP and VE resins. The material is herewith suitable for most thermoset applications, including ambient temperature curing as in: hand lay-up and spray-up application, polymer concrete manufacturing, discontinuous filament winding (pipes and storage tanks manufacturing). But also in elevated temperature (approx. 80°C) curing applications such as: continuous filament winding (pipes manufacturing), continuous lamination (corrugated and flat sheets). Furthermore Accelerator CF31 might be considered in other applications and market segments where Cobalt is an undesired component.

## Storage

Accelerator CF31 is stable at ambient temperatures. When stored under these recommended storage conditions, Accelerator CF31 will remain within the Nouryon specifications for a period of at least 6 months after delivery.

## Packaging and transport

The standard packaging is a 30 l HDPE can (Nourytainer) for 25 kg. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative.

## Safety and handling

Keep containers tightly closed. Store and handle Accelerator CF31 in a dry well-ventilated area at ambient temperatures. Do not mix with organic peroxides. Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Accelerator CF31. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at [nouryon.com/sds-search](http://nouryon.com/sds-search)

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Nourytainer and Butanox are registered trademarks of Nouryon Chemicals B.V. or affiliates in one or more territories.

## Contact Us

**Polymer Catalysts Americas**  
[polymer.amer@nouryon.com](mailto:polymer.amer@nouryon.com)

**Polymer Catalysts Europe, Middle East, India and Africa**  
[polymer.emeia@nouryon.com](mailto:polymer.emeia@nouryon.com)

**Polymer Catalysts Asia Pacific**  
[polymer.apac@nouryon.com](mailto:polymer.apac@nouryon.com)

The logo for Nouryon, featuring a stylized blue 'N' followed by the word 'ouryon' in a blue sans-serif font.