

Alcoguard 5800

HASE rheology modifier

Hydrophobically modified alkali swellable emulsion.

Specifications

Appearance	White emulsion
рН	2.5-3.5
Solid content	29-31 %
Solution viscosity	12500 - 22500 cps

Characteristics

Density	1.060 g/cc, 8.82 lbs./gallon at 25°C
Specific Gravity	1.06 at 25°C

Notes:

Applications

Alcoguard® 5800 is an associative acrylic rheology modifierdesigned to function in dispersions or detergents with high levels of surfactants or electrolytes that adversely affect other thickeners. When neutralized to a pH above 7.0, Alcoguard® 5800 exhibits highly efficient thickening and stabilization performance in a variety of aqueous systems. In some detergents the thickening effect may be achieved at pH significantly below 7 with the proper formulation technique. Incorporate Alcoguard® 5800 with mixing as last ingredient prior to neutralization. Thickener may be diluted with water to facilitate incorporation in highly viscous formulations. Thickening occurs when the pH of the formulation is raised above a pH of 7.0. Rheology modifier for surfactant systems.

Additional information

Improves flow and rheology of formulated coatings. Easy to handle, supplied as a low viscosity emulstionsynergistic thickening with anionic and non-ionic surfactants. Imparts pseudoplastic flow characteristics. Effecient in lower solids latex and pigmented systmens. Thickening above pH 7Use levels of 0.2 - 1% Alcoguard® 5800 is typically used at levels 0.2-1.0 % (dry)based on total formulation weight.

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Alcoquard® is a registered trademark in many countries. For more information, please visit our website at www.nouryon.com.

