

# Alcogum SL 920

## HASE rheology modifier

Acrylate based emulsion copolymer, hydrophobically modified, alkali soluble emulsion polymer, array of applications.

### Specifications

pH	2.5-3.5
Solid content	29-31 %

### Characteristics

Appearance	White emulsion at 25°C
Density	8.83 lbs/US gal at 25°C
Specific Gravity	1.06 g/cc at 25°C
Viscosity	≤ 200 cps at 25°C, 12,500 – 22,500 cPs, 1.0% (dry),(pH 9.0, NH4OH, 25°C, 10 rpm)

#### Notes:

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

### Applications

Add the emulsion slowly to the solution with good agitation, preferably as the last ingredient prior to neutralization. Dilution of the ALCOGUM SL 920 with water can facilitate incorporation in viscous and/or alkaline formulations. Optimum viscosity build occurs at or above pH 8. For consistent performance avoid partial neutralization and poor mixing. 0.219 parts Ammonium Hydroxide (28% ) to 1.0 part ALCOGUM SL 920 (as received)0.130 parts Sodium Hydroxide (50%) to 1.0 part ALCOGUM SL 920 (as received) High efficiency rheology modifier, surfactant synergy.

### Storage

ALCOGUM SL 920 is available in bulk, intermediate bulk and 55-gallon drums. Storage tanks should be plastic, fiberglass, or 316 stainless. Pumps should be low-shear type, such as diaphragm or peristaltic type with all wetted parts and lines being stainless steel, plastic or Teflon . Mild steel, copper, brass and aluminum should not be used. Filtering should be under low shear and volume flow conditions. Freezing should be avoided as it destabilizes the emulsion. The recommended storage temperature is 5-50°C (40-120°F). Dilution or pH adjustment of the product may require additional preservative to prevent biological growth. Keep containers tightly sealed to the prevent emulsion from air drying and forming a film. Teflon is a registered trademark of E.I. Dupont De Nemours & Co.

### Safety and handling

ALCOGUM SL 920 is listed on the TSCA confidential inventory. Contains no alkylphenol ethoxylate components.

## **Additional information**

Highly efficient viscosity build. Compatible with anionic and nonionic surfactants. Synergistic interaction with nonionic surfactants. Liquid for ease of handling and metering. Provides clear solutions and gels.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

ALCOGUM is a registered trademark in many countries. For more information, please visit our website at [www.nouryon.com](http://www.nouryon.com).

The logo for Nouryon, featuring a stylized blue 'N' followed by the word 'ouryon' in a blue sans-serif font.