

Armeen HTM-97

Primary Amine

Armeen HTM-97

Specifications

Amine number	207-217 mg KOH/g
Color	≤ 3 (1963) Gardner
Iodine value	≤ 5 g I ₂ /100 g
Moisture	≤ 0.5 %
Neutralization equivalent	259-271 g/eq
Primary Amine	≥ 97 %
Secondary Amine	≤ 3 %

Characteristics

Appearance	Solid at 25°C
Cloud point	45°C
Equivalent mass	263 g/eq
Flash point	≥150°C
HLB	8.2 (Davies scale 0-40)
Initial boiling point	275 (760 mm Hg) °C
Latent heat of fusion	~ 261.8 J/g
Melting point	56 °C
Pour point	43 °C
Specific Gravity	0.795 (60°C), 0.791 (70°C)
Specific Heat BTU/Lb/F	0.54 (113-120)
Viscosity	41.4 (65°C), 38.8 (75°C) SSU

Notes:

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

ARMEEN is a registered trademark in many countries.

Contact Us

USA and Canada

Global Headquarters
Chicago
USA
+1 312 544 7000
ansc-cs@nouryon.com

China

Regional Headquarters
Shanghai
China
+86 21 2220 5000
surfactants.asia@nouryon.com

Europe

Regional Headquarters
Stenungsund
Sweden
+46 303 850 00
surfactants.europe@nouryon.com

South East Asia

Regional Headquarters
Singapore
+65 6635 5183
surfactants.asia@nouryon.com

South America

Regional Sales Office
Itupeva
Brazil
+55 11 4591 8938

The Nouryon logo consists of the word "Nouryon" in a bold, orange, sans-serif font. The letter "N" is stylized with a white negative space cutout.