

Armostat 1800-XP75

(Hydrogenated tallow)-bis(2-hydroxyethyl) amine

Semi-permanent, vegetable-based alternative for Armostat 600. A 75% concentration of Armostat 1800 on a polypropylene carrier.

CAS number 90367-28-5, 9003-07-0
EINECS/ELINCS No. 233-520-3

TSCA status
listed on inventory

Specifications

Additive content	73-77 %
Appearance	Off-white granules

Characteristics

Bulk density	430-530 kg/m ³
Density	0.95 g/cm ³
Melting point	≥ 120 °C

Storage

Nouryon recommends to store Armostat 1800-XP75 in a dry, well-ventilated place at 25°C (77°F) max.

Note

When stored under the recommended storage conditions, Armostat 1800-XP75 will remain within the Nouryon specifications for a period of at least 12 months after delivery.

Packaging and transport

The standard packaging is 25 kg (55.1 lb) net in a PE bag in a cardboard box. A full pallet carries 600 kg (1323 lb) net. Both packaging and transport meet the international regulations. Please refer to the Material Safety Data Sheet (MSDS) section 14 for transport safety information. For the availability of other packed quantities contact your Nouryon representative.

Safety and handling

Please refer to the Material Safety Data Sheet (MSDS) for detailed information on the safe storage, use and handling of Armostat 1800-XP75. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available at nouryon.com/sds-search.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Armostat is a registered trademark of Nouryon Chemicals B. V. or affiliates in one or more territories.

Contact Us

Polymer Catalysts Americas
polymer.amer@nouryon.com

Polymer Catalysts Europe, Middle East, India and Africa
polymer.emeia@nouryon.com

Polymer Catalysts Asia Pacific
polymer.apac@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font.