

Armostat 600-XP75

(Hydrogenated tallow)-bis(2-hydroxyethyl) amine

Hydrogenated tallow-based antistat typically used in BOPP and PP. Provides sustained antistatic properties and shows excellent thermal stability due to its saturated alkyl chain, making it especially suitable for applications needing higher processing temperatures. 75% Armostat 600 on a polypropylene carrier.

CAS number 90367-28-5, 9003-07-0
EINECS/ELINCS No. 291-276-3

TSCA status
not listed on inventory

Specifications

Additive content	73-77 %
Appearance	Off-white granules

Characteristics

Bulk density	430-530 kg/m ³
Density	0.95 g/cm ³
Melting point	≥ 120 °C

Applications

Armostat 600-XP75 is a solid high concentrate consisting of 75% Armostat 600, a semi-permanent, animal based antistat on a polypropylene carrier. Armostat 600 is an internal antistatic additive that can be used in various polymers such as PP, and BOPP.

Storage

Nouryon recommends to store Armostat 600-XP75 in a dry, well-ventilated place at 25°C (77°F) max.

Note

When stored under the recommended storage conditions, Armostat 600-XP75 will remain within the Nouryon specifications for a period of at least 12 months after delivery.

Packaging and transport

The standard packaging is a 25 kg (55.1 lb) net PE bag in a cardboard box. A full pallet carries 600 kg (1323 lb) net. Both packaging and transport meet the international regulations. Please refer to the Safety Data Sheet (SDS) section 14 for transport safety information. For the availability of other packed quantities contact your Nouryon representative.

Safety and handling

Please refer to the Material Safety Data Sheet (MSDS) for detailed information on the safe storage, use and handling of Armostat 600-XP75. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available at nouryon.com/sds-search.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Armostat is a registered trademark of Nouryon Chemicals B. V. or affiliates in one or more territories.

Contact Us

Polymer Catalysts Americas
polymer.amer@nouryon.com

Polymer Catalysts Europe, Middle East, India and Africa
polymer.emeia@nouryon.com

Polymer Catalysts Asia Pacific
polymer.apac@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font. The 'N' is significantly larger and more prominent than the rest of the text.