

# Armostat 600V

Vegetable-based saturated alkylbis(2-hydroxyethyl) amine

Antistatic agent. Vegetable-based alternative to Armostat® 600. Provides sustained antistatic properties and shows excellent thermal stability due to its saturated alkyl chain, making it especially suitable for applications needing higher processing temperatures. Typically used in BOPP and PP.

**CAS number**  
90367-28-5

**EINECS/ELINCS No.**  
291-276-3

**Molecular weight**  
352

## Applications

Armostat® 600V is a palm based saturated alkylbis(2-hydroxyethyl) amine. Armostat® 600V is an internal antistatic additive that can be used in various polymers such as PE, LLDPE, PP, SAN and ABS. Armostat® 600V gives sustained antistatic action and shows excellent thermal stability due to its saturated alkyl chain. This makes Armostat® 600V especially suitable for those applications needing higher processing temperatures. Armostat® 600V is a solid at ambient temperatures. When heated at 50-55°C the product can be dosed as a liquid directly into the polymer by using a single or twinscrew extruder. Pigment or color concentrates should be mixed with the antistatic agent prior to extruding. Premixing ensures uniform distribution of Armostat® 600V in the resin while Armostat® 600V acts as a dispersion aid to the pigment color concentrate.

## Storage

Nouryon recommends to store Armostat® 600V in a dry well-ventilated place at 25°C (77°F) max. Prolonged storage over 60°C (140°F) can cause some discoloration.

### Note

When stored under the recommended storage conditions, Armostat® 600V will remain within the Nouryon specifications for a period of at least 12 months after delivery.

## Packaging and transport

The standard packaging is 180 kg net in a steel drum. A full pallet carries 720 kg net. Bulk delivery is also possible. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative.

## Safety and handling

Please refer to the Material Safety Data Sheet (MSDS) for detailed information on the safe storage, use and handling of Armostat® 600V. This information should be thoroughly reviewed prior to acceptance of this product.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Armostat® is a registered trademark of Nouryon Chemicals B. V. or affiliates in one or more territories.

# Nouryon