

BERMOCOLL CCA 912

BERMOCOLL CCA 912 is a modified non-ionic, water soluble cellulose ether. It improves the consistency and the water retention of gypsum and cement based plasters.

Specifications

Appearance	Whitish powder
Particle size	98 % \leq 300 μ m
Water content	\leq 4 %

Characteristics

Surface activity	Weak
Viscosity at 20 °C (Brookfield LV), 1% solution	2200-3000 mPa.s

Notes:

BERMOCOLL CCA 912 is a modified high viscosity grade of ethyl hydroxyethyl cellulose.

Applications

BERMOCOLL CCA 912 is used as an admixture in gypsum and cement based plasters for improvement of workability, consistency and water retention. BERMOCOLL CCA 912 prolongs the open time and effectively counteracts the sagging tendency of the plaster. BERMOCOLL CCA 912 should be admixed to the plaster in dry form before the water is added. Normal dosage is 0.15 - 0.30 % calculated on the dry mix. Due to its small particle size BERMOCOLL CCA 912 will dissolve rapidly after addition of water to the dry mix.

Storage

In unopened bags, BERMOCOLL CCA 912 can be stored for several years. In opened bags, the moisture content of BERMOCOLL CCA 912 will be influenced by the air humidity. At the temperatures above 250 °C (480 °F), charring of BERMOCOLL CCA 912 will occur.

Packaging and transport

Like many industrial processed powdery materials, cellulose ether dusts are combustible and can cause dust explosions. Dust formation must be avoided or kept to a minimum. Care should be taken to prevent ignition from heat, spark, open flames or hot surface. BERMOCOLL CCA 912 is packed in a polyethylene bag. Net weight 20 kg. We recommend emptying the bags from the bottom. The empty bags can be recycled or burned. In unopened bags, BERMOCOLL CCA 912 can be stored for several years. In opened bags, the moisture content of BERMOCOLL CCA 912 will be influenced by the air humidity. At the temperatures above 250°C (480°F), charring of BERMOCOLL CCA 912 will occur. At high temperatures and in contact with an open flame, BERMOCOLL CCA 912 will burn slowly with the characteristics of cellulose.

Safety and handling

At high temperatures and in contact with an open flame, BERMOCOLL CCA 912 will burn slowly with the characteristics of cellulose.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

For more information, please visit our website at www.nouryon.com.

