

Bermocoll EM 7000 FQ

Methyl ethyl hydroxyethyl cellulose

Bermocoll® EM 7000 FQ is a non-ionic, water soluble cellulose ether. It improves the consistency, the stability, and the water retention of water based products.

Specifications

Appearance	Whitish powder
Particle size	98 % ≤ 500 µm
Salt content	≤ 6 %
Water content	≤ 4 %

Characteristics

pH, 1% solution	5-7
Surface activity	Weak
Viscosity at 20 °C (Brookfield LV), 1% solution	6000-8000 mPa.s

Notes:

Bermocoll® EM 7000 FQ is a high viscosity grade of methyl ethyl hydroxyethyl cellulose.

Applications

Bermocoll® EM 7000 FQ is used in latex paints for thickening and stabilizing effects. Normal dosage in paints is 0.2 - 0.5 % calculated on the total paint weight. Bermocoll® EM 7000 FQ is easily dispersed in cold water of pH7 or less. Bermocoll® EM 7000 FQ can form lumps when added to an alkaline liquid. To avoid this, it should be added as a ready stock solution, as a slurry in slight acid water or in an organic solvent, or as a dry mix with other powder materials.

Storage

In unopened bags, Bermocoll® EM 7000 FQ can be stored for several years. In opened bags, the moisture content of Bermocoll® EM 7000 FQ will be influenced by the air humidity. At the temperatures above 250,°C (480,°F), charring of Bermocoll® EM 7000 FQ will occur.

Packaging and transport

Like many industrial processed powdery materials, cellulose ether dusts are combustible and can cause dust explosions. Dust formation must be avoided or kept to a minimum. Care should be taken to prevent ignition from heat, spark, open flames or hot surface. Bermocoll® EM 7000 FQ is packed in polyethylene plastic bags. Net weight 20 kg. We recommend emptying the bags from the bottom. The empty bags can be recycled or burned.

Safety and handling

At high temperatures and in contact with an open flame, Bermocoll® EM 7000 FQ will burn slowly with the characteristics of cellulose.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

For more information, please visit our website at www.nouryon.com.

The logo for Nouryon, featuring a stylized blue 'N' followed by the word 'ouryon' in a blue sans-serif font.