

# Cadox L-50a Red

Methyl ethyl ketone peroxide

Special purpose catalyst for curing tooling gel coats and promoted unsaturated polyester resins. Low-hydrogen peroxide & high dimer content reduces gel-coat porosity and provides improved curing of vinylester resins.

**CAS number**  
1338-23-4

**EINECS/ELINCS No.**  
215-661-2

**TSCA status**  
listed on inventory

## Specifications

Appearance, 20-25°C	Red liquid
Total active oxygen	8.9 %

## Characteristics

Density, 20 °C	1.0 g/cm <sup>3</sup>
----------------	-----------------------

## Applications

Cadox® L-50a Red is an ideal catalyst for the room temperature cure of promoted unsaturated polyester resins. Cadox® L-50a Red has a low hydrogen peroxide content which reduces gel coat porosity and provides improved curing of vinyl ester resins. Cadox® L-50a Red also has a high MEKP dimer content which may provide better final cure in some resin systems. Additional end-use information is available in Nouryon's brochures.

## Thermal stability

Organic peroxides are thermally unstable substances, which may undergo self-accelerating decomposition. The lowest temperature at which self-accelerating decomposition of a substance in the original packaging may occur is the Self-Accelerating Decomposition Temperature (SADT). The SADT is determined on the basis of the Heat Accumulation Storage Test.

SADT	60°C (140°F)
Method	The Heat Accumulation Storage Test is a recognized test method for the determination of the SADT of organic peroxides (see Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria - United Nations, New York and Geneva).

## Storage

Due to the relatively unstable nature of organic peroxides a loss of quality can be detected over a period of time. To minimize the loss of quality, Nouryon recommends a maximum storage temperature (Ts max. ) for each organic peroxide product.

Ts Max.	30°C (86°F)
Note	When stored under these recommended storage conditions, Cadox® L-50a Red will remain within the Nouryon specifications for a period of at least three months after delivery.

## Packaging and transport

Cadox® L-50a Red is packed in non-returnable, 1 gallon polyethylene containers of 8 lb net weight (4 per case) and in 5 gallon polyethylene containers of 40 lb net weight. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Cadox® L-50a Red is classified as Organic peroxide type D; liquid; Division 5. 2; UN 3105; PG II.

## Safety and handling

Keep containers tightly closed. Store and handle Cadox® L-50a Red in a dry well-ventilated place away from sources of heat or ignition and direct sunlight. Never weigh out in the storage room. Avoid contact with reducing agents (e. g. amines), acids, alkalis and heavy metal compounds (e. g. accelerators, driers and metal soaps). Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Cadox® L-50a Red. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at [nouryon.com/sds-search](http://nouryon.com/sds-search).

## Major decomposition products

Carbon dioxide, Water, Acetic acid, Formic acid, Propionic acid, Methyl ethyl ketone

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Cadox® is a registered trademark of Nouryon Chemicals B. V. or affiliates in one or more territories.

## Contact Us

**Polymer Specialties Americas**  
polymer.amer@nouryon.com

**Polymer Specialties Europe, Middle East, India and Africa**  
polymer.emeia@nouryon.com

**Polymer Specialties Asia Pacific**  
polymer.apac@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font. The 'N' is significantly larger and more prominent than the rest of the text.