Diethyleneglycol Mixture CN (DEG Mix CN)

DEG-Mix CN is a mix of diethylene glycol, monoethylene glycol, triethylene glycol and water. Its main application is as a raw material for grinding aids. CAS number EINECS/ELINCS No. 111-46-6 (DEG) / 107-21- 203-872-2 (DEG) / 203-1 (MEG) 473-3 (MEG)

Molecular weight Molecular formula 106.1 gmol-1 (DEG) $C_4H_{10}O_3$

Specifications

Appearance (MOA 200)	Dark brown/black liquid
Diethylene glycol (EO498C)	>50 wt%
Monoethylene glycol (EO498C)	Reported value
Triethylene glycol (EO498C)	Reported value
Water (MOA 208)	<10 wt%

Characteristics

Form	Viscous liquid
Color	Dark
Odor	Odorless
Explosive properties	No
Flammability, liquids	Not classified as a flammability hazard
Oxidizing properties	No
Water solubility	Partly soluble
pH, 1% solution	11
Melting point/freezing point, 1013 hPa	<-20 °C
Boiling point/boiling range, 1013 hPa	>100 °C
Flash point, 1013 hPa	100-199 ℃
Ignition temperature	>100 °C
Vapor pressure, 25°C	0,028 hPa
Density, 20°C	1130 kg/m³
Relative density, 20°C	1,13
Dynamic viscosity, 20°C	20 mPa.s

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

For more information, please visit our website at www.nouryon.com.

