

# Nouryact CF12N

## Metal complex

Nouryact CF12N is a copper-based accelerator used for curing UP resins, acrylic and vinylester resins at ambient temperatures.

CAS number  
142-71-2

EINECS/ELINCS No.  
205-553-3

TSCA status  
listed on inventory

### Specifications

Appearance	Clear green liquid
Copper	1.50-1.70 %

### Characteristics

Density, 20 °C	1.09 g/cm <sup>3</sup>
----------------	------------------------

### Applications

Nouryact CF12N can be used in combination with Butanox M-50 in an ambient temperature curing system for hand lay-up and spray-up application, polymer concrete manufacturing, storage tank manufacturing, other applications and market segments where Cobalt is an undesired trace element.

### Storage

Nouryact CF12N is stable at ambient temperatures.

#### Note

When stored under these recommended storage conditions, Nouryact CF12N will remain within the Nouryon specifications for a period of at least 6 months after delivery.

### Packaging and transport

The standard packaging is a 30 l HDPE can (Nourytainer) for 25 kg. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Nouryact CF12N is classified as Environmentally hazardous substance, liquid, toxic, n. o. s. ; Class 8; UN 1760.

### Safety and handling

Keep containers tightly closed. Store and handle Nouryact CF12N in a dry well-ventilated area at ambient temperatures. Do not mix with organic peroxides. Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Nouryact CF12N. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at [nouryon.com/sds-search](http://nouryon.com/sds-search).

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Nouryact, Nourytainer, Butanox and BluCure are registered trademarks of Nouryon Functional Chemicals B.V. or affiliates in one or more territories.

## Contact Us

Polymer Catalysts Americas  
[polymer.amer@nouryon.com](mailto:polymer.amer@nouryon.com)

Polymer Catalysts Europe, Middle East, India and Africa  
[polymer.emeia@nouryon.com](mailto:polymer.emeia@nouryon.com)

Polymer Catalysts Asia Pacific  
[polymer.apac@nouryon.com](mailto:polymer.apac@nouryon.com)

The Nouryon logo consists of a stylized orange 'N' followed by the word 'ouryon' in a lowercase, sans-serif font, all in orange.