

Nouryact CF30

Metal complex

Nouryact® CF30 is an iron-based accelerator used for curing UP resins, acrylic and vinylester resins at elevated temperatures.

CAS number
proprietary

Specifications

Appearance	Orange clear liquid
Iron	40 mg/kg

Applications

Nouryact® CF30 has high reactivity in particular at elevated temperature curing (80°C) in 4 mm glass fiber reinforced laminates. It offers: high reactivity in 4 mm laminates for curing at elevated temperature, high reactivity in SPI testing at ambient temperature specifically in isophthalic resins, reduction of activation temperature of peroxyesters, fast curing and low residual styrene levels in curing agglomerated stone slabs process at elevated temperature, sufficiently long pot-life in medium reactive ortho resins as is required in the agglomerated stone process.

Storage

Nouryact® CF30 is stable at ambient temperatures.

Note	When stored under these recommended storage conditions, Nouryact® CF30 will remain within the Nouryon specifications for a period of at least 6 months after delivery.
------	--

Packaging and transport

The standard packaging is a 30 l HDPE can (Nourytainer®) for 25 kg. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative.

Safety and handling

Keep containers tightly closed. Store and handle Nouryact® CF30 in a dry well-ventilated area at ambient temperatures. Do not mix with organic peroxides. Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Nouryact® CF30. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at nouryon.com/sds-search.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Nouryact®, Nourytainer®, Butanox® and Trigonox are registered trademarks of Nouryon Functional Chemicals B.V. or affiliates in one or more territories.

Contact Us

Polymer Specialties Americas
polymer.amer@nouryon.com

Polymer Specialties Europe, Middle East, India and Africa
polymer.emeia@nouryon.com

Polymer Specialties Asia Pacific
polymer.apac@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font. The 'N' is significantly larger and more prominent than the rest of the text.