

Nouryact CF40

Metal complex

Nouryact® CF40 is an iron-based accelerator used for curing UP resins, acrylic and vinylester resins at ambient and elevated temperatures.

CAS number
proprietary

Specifications

Appearance	Clear yellow liquid
Iron	800-900 mg/kg

Characteristics

Density, 20 °C	1.07 g/cm ³
Solvent	Hydroxy ethyl methacrylate
Viscosity, 20 °C	7 mPa.s

Applications

Nouryact® CF40 can be best used in combination with a hydroperoxide like Trigonox K-90 for efficient curing at ambient and elevated temperature for curing most commonly used UP, VE and DCPD resins.

Storage

Nouryact® CF40 is stable at ambient temperatures.

Note

When stored under these recommended storage conditions, Nouryact® CF40 will remain within the Nouryon specifications for a period of at least 6 months after delivery.

Packaging and transport

The standard packaging is a 30 l HDPE can (Nourytainer®) for 25 kg. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Nouryact® CF40 is not regulated as a dangerous good.

Safety and handling

Keep containers tightly closed. Store and handle Nouryact® CF40 in a dry well-ventilated area at ambient temperatures. Do not mix with organic peroxides. Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Nouryact® CF40. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at nouryon.com/sds-search.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Nouryact®, Nourytainer®, Butanox®, Trigonox and BluCure are registered trademarks of Nouryon Functional Chemicals B.V. or affiliates in one or more territories.

Contact Us

Polymer Specialties Americas
polymer.amer@nouryon.com

Polymer Specialties Europe, Middle East, India and Africa
polymer.emeia@nouryon.com

Polymer Specialties Asia Pacific
polymer.apac@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font.