

Structure 2020 polymer

ASE rheology modifier

Polymeric thickening agents for alcohol-based hand sanitizers.

INCI name

Acrylates Crosspolymer-6

Specifications

pH	2.2-3
Solid content	29-31 %
Viscosity	10000-15000 (pH 9.0, NaOH, 25°C, 10 rpm, 2.5% (dry)) cps

Characteristics

Appearance	White Emulsion at 20°C
Density	8.82 lbs/US gal. at 25°C
Specific Gravity	1.06 g/cc at 25°C
Viscosity	≤200 cps at 25°C

Notes:

Typical Data are based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

Storage

Structure® 2020 is available in bulk, intermediate bulk and 55-gallon drums. Storage tanks should be plastic, fiberglass, or 316 stainless. Pumps should be low-shear type, such as diaphragm or peristaltic type with all wetted parts and lines being stainless steel, plastic or Teflon®. Mild steel, copper, brass and aluminum should not be used. Filtering should be under low shear and volume flow conditions. Freezing should be avoided as it destabilizes the emulsion. The recommended storage temperature is 5-50°C (40-120°F). Dilution or pH adjustment of the product may require additional preservative to prevent biological growth. Keep containers tightly sealed to prevent emulsion from air drying and forming a film. Teflon® is a registered trademark of E.I. DuPont De Nemours & Co.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Structure® is a registered trademark in many countries. For more information, please visit our website at www.nouryon.com.

The logo for Nouryon, featuring a stylized blue 'N' followed by the word 'ouryon' in a blue sans-serif font.