


# Trigonox 23-CL75

tert-Butyl peroxyneodecanoate, 75% solution in isoparaffin



Trigonox 23-CL75 is a polymerization initiator (75% active ingredient in Isopar L) for (co)polymerization of ethylene, vinylacetate, vinyl chloride and vinylidene chloride.

CAS number  
26748-41-4

EINECS/ELINCS No.  
247-955-1

TSCA status  
listed on inventory

Molecular weight  
244.4

Active oxygen content  
peroxide  
6.55%

## Specifications

Active oxygen	4.84-4.98 %
Appearance	Clear liquid
Assay	74.0-76.0 %
Color	≤ 30 Pt-Co / APHA
Hydroperoxides as TBHP	0.10 %
Inorganic + organic hydrolysable chloride	≤ 150 mg/kg

## Characteristics

Density, 0 °C	0.877 g/cm <sup>3</sup>
Viscosity, 0 °C	17 mPa.s

## Applications

Polymerization of ethylene: Trigonox 23-CL75 is an efficient initiator for the production of Low Density Polyethylene (LDPE). It is used both for tubular and autoclave processes. In most cases a combination with other peroxides is used to ensure a broad reactivity range. Trigonox 23-CL75 is a highly reactive initiator for curing unsaturated polyester and vinyl ester resins at elevated temperatures. It is typically used in combination with higher temperature finishing initiators in pultrusion and continuous panel applications.

## Half-life data

The reactivity of an organic peroxide is usually given by its half-life ( $t_{1/2}$ ) at various temperatures. For Trigonox 23-CL75 in chlorobenzene:

0.1 hr	at 84°C (183°F)
1 hr	at 64°C (147°F)
10 hr	at 46°C (115°F)
Formula 1	$k_d = A \cdot e^{-E_a/RT}$
Formula 2	$t_{1/2} = (\ln 2)/k_d$
E <sub>a</sub>	115.47 kJ/mole
A	1.52E+14 s <sup>-1</sup>
R	8.3142 J/mole·K
T	(273.15+°C) K

## Thermal stability

Organic peroxides are thermally unstable substances, which may undergo self-accelerating decomposition. The lowest temperature at which self-accelerating decomposition of a substance in the original packaging may occur is the Self-Accelerating Decomposition Temperature (SADT). The SADT is determined on the basis of the Heat Accumulation Storage Test.

SADT	20°C (68°F)
Emergency temperature (T <sub>e</sub> )	10°C (50°F)
Control temperature (T <sub>c</sub> )	0°C (32°F)
Method	The Heat Accumulation Storage Test is a recognized test method for the determination of the SADT of organic peroxides (see Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria - United Nations, New York and Geneva).

## Storage

Due to the relatively unstable nature of organic peroxides a loss of quality can be detected over a period of time. To minimize the loss of quality, Nouryon recommends a maximum storage temperature (T<sub>s</sub> max. ) for each organic peroxide product.

T <sub>s</sub> Max.	-10°C (14°F)
T <sub>s</sub> Min.	-20°C (-4°F) to prevent crystallization
Note	When stored under these recommended storage conditions, Trigonox 23-CL75 will remain within the Nouryon specifications for a period of at least 3 months after delivery.

## Packaging and transport

The standard packaging is a 20 kg jerrycan. Both packaging and transport meet the international regulations. For the availability of other packed quantities consult your Nouryon representative. Trigonox 23-CL75 is classified as Organic peroxide type D; liquid, temperature controlled, Division 5. 2; UN 3115.

## Safety and handling

Keep containers tightly closed. Store and handle Trigonox 23-CL75 in a dry well-ventilated place away from sources of heat or ignition and direct sunlight. Never weigh out in the storage room. Avoid contact with reducing agents (e. g. amines), acids, alkalis and heavy metal compounds (e. g. accelerators, driers and metal soaps). Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Trigonox 23-CL75. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at [nouryon.com/sds-search](http://nouryon.com/sds-search).

## Major decomposition products

Carbon dioxide, tert-Butanol, Isomers of neononane

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Trigonox is a registered trademark of Nouryon Functional Chemicals B.V. or affiliates in one or more territories.

## Contact Us

**Polymer Catalysts Americas**  
polymer.amer@nouryon.com

**Polymer Catalysts Europe, Middle East, India and Africa**  
polymer.emeia@nouryon.com

**Polymer Catalysts Asia Pacific**  
polymer.apac@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif blue font.