


Trigonox 421-MC70

1,1,3,3-Tetramethylbutyl peroxy-2-ethylhexanoate, 70% with isoparaffin



Trigonox® 421-MC70 is an initiator for (co)polymerization of ethylene, styrene, acrylates, methacrylates and polyols. Sustainable replacement for AIBN.

CAS number
22288-43-3

EINECS/ELINCS No.
244-894-2

TSCA status
listed on inventory

Molecular weight
272.4

Active oxygen content
peroxide
4.1%

Specifications

Appearance	Clear liquid
------------	--------------

Characteristics

Density, 10 °C	0.864 g/cm ³
Viscosity, 10 °C	5.9 mPa.s

Applications

Trigonox® 421-MC70 can be used to initiate the (co)polymerization of acrylates and methacrylates in the temperature range between 70°C and 120°C. Trigonox® 421-MC70 can be applied in suspension as well as in solvent and bulk polymerization. Trigonox® 421-MC70 can also be used for the copolymerization of styrene and acrylonitrile and for vinylacetate based copolymers.

Half-life data

The reactivity of an organic peroxide is usually given by its half-life ($t_{1/2}$) at various temperatures. For Trigonox® 421-MC70 in chlorobenzene half-life at other temperatures can be calculated by using the equations and constants mentioned below:

0.1 hr	109°C (228°F)
1 hr	88°C (190°F)
10 hr	69°C (156°F)
Formula 1	$k_d = A \cdot e^{-E_a/RT}$
Formula 2	$t_{1/2} = (\ln 2)/k_d$
Ea	123.80 kJ/mole
A	1.62E+14 s ⁻¹
R	8.3142 J/mole-K
T	(273.15+°C) K

Thermal stability

Organic peroxides are thermally unstable substances, which may undergo self-accelerating decomposition. The lowest temperature at which self-accelerating decomposition of a substance in the original packaging may occur is the Self-Accelerating Decomposition Temperature (SADT). The SADT is determined on the basis of the Heat Accumulation Storage Test.

SADT	30°C
Emergency temperature (T_e)	20°C
Control temperature (T_c)	15°C
Method	The Heat Accumulation Storage Test is a recognized test method for the determination of the SADT of organic peroxides (see Recommendations on the Transport of Dangerous Goods, Manual of Tests and Criteria - United Nations, New York and Geneva).

Storage

Due to the relatively unstable nature of organic peroxides a loss of quality can be detected over a period of time. To minimize the loss of quality, Nouryon recommends a maximum storage temperature (T_s max.) for each organic peroxide product.

T_s Max.	5°C
T_s Min.	-20°C to prevent crystallization
Note	When stored according to these recommended storage conditions, Trigonox® 421-MC70 will remain within the Nouryon specifications for a period of at least 3 months after delivery.

Packaging and transport

The standard packaging is a 16 kg can. Both packaging and transport meet the international regulations. For the availability of other packed quantities contact your Nouryon representative. Trigonox® 421-MC70 is classified as Organic peroxide type D; liquid, temperature controlled; Division 5.2; UN 3115.

Safety and handling

Keep containers tightly closed. Store and handle Trigonox® 421-MC70 in a dry well-ventilated place away from sources of heat or ignition and direct sunlight. Never weigh out in the storage room. Avoid contact with reducing agents (e.g. amines), acids, alkalis and heavy metal compounds (e.g. accelerators, driers and metal soaps). Please refer to the Safety Data Sheet (SDS) for further information on the safe storage, use and handling of Trigonox® 421-MC70. This information should be thoroughly reviewed prior to acceptance of this product. The SDS is available at nouryon.com/sds-search.

Major decomposition products

Carbon dioxide, 2,2-Dimethylpropane, Acetone, Heptane, Heptenes, 2,4,4-Trimethyl-2-pentanol, 2-(1-Ethylpentoxy)-2,4,4-trimethylpentane

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Trigonox® is a registered trademark of Nouryon Functional Chemicals B.V. or affiliates in one or more territories.

Contact Us

Polymer Specialties Americas
polymer.amer@nouryon.com

Polymer Specialties Europe, Middle East, India and Africa
polymer.emeia@nouryon.com

Polymer Specialties Asia Pacific
polymer.apac@nouryon.com

The Nouryon logo consists of a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font. The 'N' is significantly larger and more prominent than the rest of the text.