



Product specification Expancel MB

Expancel	Grade of microspheres	Concentration of microspheres	Carrier	Height of foaming ⁽¹⁾ mm	Bulk density g/l
920 MB 120	920-120	65 ± 1	EVA*	90–140 (200°C)	400–500
930 MB 120	930–120	65 ± 1	EVA*	100–150 (200°C)	400–500
950 MB 80	950-80	65 ± 1	EVA*	90–130 (210°C)	400–500
951 MB 120	951-120	65 ± 1	EVA*	100–150 (210°C)	400–500

New product

980 MB 100	980-100	65 ± 1	EVA*	70–110 (210°C)	400–500
------------	---------	--------	------	----------------	---------

Product information

- Expancel MB = Masterbatch with unexpanded Expancel Microspheres
- *EVA = Copolymer of ethylene vinylacetate
- Use the product within three years after production date, if unopened.
- Not all grades available in all locations. Check local sales office for availability.

References

- 1) **Height of foaming:** measurement of the height of foam, given by free expansion of Expancel MB. Performed in a conventional hot air oven. More information: "Analytical method QMS-56".

To find out more about our microspheres,
visit our website:
nouryon.com/products/expancel-microspheres

or contact us at:
E: info.expancel@nouryon.com



The information contained in this leaflet is not intended to be exhaustive and is presented in good faith and believed to be correct as of the date on which it is prepared. Persons using the information must make their own determinations and assessments as to the suitability of the relevant information for their purposes prior to taking any action based on the information. Neither Nouryon nor any of its affiliates or representatives makes any representation or warranty, expressed or implied, as to the accuracy or completeness of this document or any of the information contained herein. Nouryon and its affiliates or representatives expressly disclaim to the fullest extent permitted by law any and all liability based, in whole or in part, on the document or any information contained herein.

2021-06

Expancel® is a registered trademark of Nouryon in a number of territories worldwide.