



Product Specification Expancel Microspheres

February, 2019 (replaces 2017.09)


Expancel WE

Expancel	Estimated particle Size, μm D(0.5)	Solid content ⁽¹⁾ %	True density ⁽²⁾ kg/m^3	True volume ⁽¹⁾ l/kg	Solvent Resistance ⁽³⁾
461 WE 20 d36	20–30	15 ± 2	36 ± 4	$4,2 \pm 0,45$	3
461 WE 40 d36	30–50	15 ± 2	36 ± 4	$4,2 \pm 0,45$	3
921 WE 40 d24	35–55	$10 \pm 1,5$	24 ± 3	$4,2 \pm 0,45$	5

- Expancel WE = Wet Expanded Expancel Microspheres
- Packed on pallets with 20 polyethylene bags, each bag with a net weight of 10 kg. Volume approx 1.5 m³, incl pallet.
- Use the product within two years after production date, if unopened.
- Not all grades available in all locations. Check local sales office for availability.

More information:

- 1) "Analytical method no 22"
- 2) "Density measurements of Expancel MS"
- 3) "Chemical resistance of Expancel MS"

The top half of the page features two thin, curved orange lines that sweep across the frame. A small teal dot is positioned on the upper curve, and a small purple dot is on the lower curve.

For more information on our
microspheres you can contact us at:

E: info.expancel@nouryon.com

Nouryon
Expancel
Box 13000
SE-850 13 Sundsvall
Sweden
T: +46-60 13 40 00

nouryon.com
expancel.com

Nouryon