

## Redicote® C-450-1

Emulsifier for cationic quick set bitumen emulsions for slurry and micro surfacing. Break retarder for quick set slurry surfacing and micro surfacing.

### Benefits and features

- High reactive aggregates:**  
 Cationic quick-set emulsions made with Redicote C-450-1 provide mix time even with reactive aggregates and in hot weather conditions
- Medium and low reactive aggregates:**  
 Used together with Redicote C-471 it provides emulsion recipes suitable for a wide range of aggregate reactivity and field conditions
- Water-soluble:**  
 Its low viscosity and water solubility make it an ideal break retarder for slurry systems
- Micro surfacing:**  
 Emulsions formulated with Redicote C-450-1 can meet specifications for micro surfacing as well as quick-set slurry surfacing

### Storage and handling

Redicote C-450-1 may be stored in carbon steel tanks. Bulk storage should be maintained at 25-50°C (77-122°F). Avoid extended heating above 65°C (150°F). Protect against exposure to moisture. Redicote C-450-1 contains amines and may cause severe irritation or burns to skin and eyes. Protective gloves and safety goggles must be worn when handling this product. For further information consult the Safety Data Sheet.

### Packaging information

Redicote C-450-1 is available in bulk shipment, in tight head steel drums of 400 lbs (181 kg) net weight, or in one-way totes (IBCs) of 2000 lbs (907 kg) net weight.

### Dosage

Cationic quick set emulsion	0.7-1.5%	pH 1-3 hydrochloric acid
-----------------------------	----------	-----------------------------

### Specification

Amine value, mg KOH/g	445-485	SMA CL002
Water, %	max 1	SMA CL007

### Physical properties

Appearance at 25°C	liquid
Flash point, °C	200 (392°F)
Pour point, °C	-5 (23°F)

	10	20	30	40	°C
	50	68	86	104	°F
Density, g/cc	0.97	0.96	0.96	0.95	
Density, lbs/U.S. gal	8.08	8.04	8.00	7.96	
Viscosity, mPa s (cP)	8700	3100	1350	650	

Physical properties are typical data based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

For more information and sample formulations contact us at [asphalt@nouryon.com](mailto:asphalt@nouryon.com).

**USA and Canada**

Chicago, USA  
T +1 800 906 9977

**South America**

Itupeva, Brazil  
T +55 11 4591 8938

**Central America  
and Caribbean**

Mexico City, Mexico  
T +52 55 5261 7895

**China**

Shanghai, China  
T +86 21 2220 5000

**South East Asia**

Singapore  
T +65 6635 5183

**India**

Mumbai, India  
T +91 22 6842 6700

**Europe**

Stenungsund, Sweden  
T +46 303 850 00

**Middle East**

Dubai, United Arab Emirates  
T +971 4247 1500

**Russia**

Moscow, Russia  
T +7 495 766 1606

All information concerning our products and/or all suggestions for handling and use contained herein (including formulation and toxicity information) are offered in good faith and are believed to be reliable. However, Nouryon makes no warranty express or implied (i) as to the accuracy or sufficiency of such information and/or suggestions, (ii) as to any product's merchantability or fitness for a particular use or (iii) that any suggested use (including use in any formulation) will not infringe any patent. Nothing contained herein shall be construed as granting or extending any license under any patent. The user must determine for itself by preliminary tests or otherwise the suitability of any product and of any information contained herein (including but not limited to formulation and toxicity information) for the user's purpose. The safety of any formulations described herein has not been established. The suitability and safety of a formulation should be confirmed in all respects by the user prior to use. The information contained herein supersedes all previously issued bulletins on the subject matter covered.

Products mentioned are trademarks of Nouryon and registered in many countries.

**About Nouryon**

We are a global specialty chemicals leader. Markets worldwide rely on our essential chemistry in the manufacture of everyday products such as paper, plastics, building materials, food, pharmaceuticals, and personal care items. Building on our nearly 400-year history, the dedication of our 10,000 employees, and our shared commitment to business growth, strong financial performance, safety, sustainability, and innovation, we have established a world-class business and built strong partnerships with our customers.

We operate in over 80 countries around the world and our portfolio of industry-leading brands includes Eka, Dissolvine, Trigonox, and Berol.

For more information visit [nouryon.com](http://nouryon.com).

**Nouryon**