



## Redicote<sup>®</sup> E-11 E

Emulsifier for cationic slow set bitumen emulsions for tack, prime, slurry seal and cold mix applications. Emulsifier for oils and resins used for dust control and rejuvenating. Break retarder for slurry.

### Benefits and features

- Low use level**  
 Good quality slow set emulsions are formed at low use level
- Easy handling**  
 The low viscosity, low pour point and water solubility of Redicote E-11 E makes it easy to use both as emulsifier and as a break control additive (retarder) for slurry
- Good adhesion**  
 Emulsions made with Redicote E-11 E pass the particle charge test and provide good adhesion to siliceous aggregates
- No need for acid**  
 No acid is required for soap preparation. The neutral pH of the emulsion is preferred in applications like tack coats for concrete, when emulsifying biobased binders and when water soluble thickeners are incorporated.

### Storage and handling

Redicote E-11 E contains ethanol, keep away from sources of ignition. Redicote E-11 E contains water and chloride ion and 316 and 317L stainless steels or glass or polymer lined tanks are recommended. Bulk storage need not be heated. Redicote E-11 E contains quaternary amines and may cause severe irritation or burns to skin and eyes. Protective goggles and gloves must be worn when handling this product. For further information consult the Safety Data Sheet.

### Dosage

Cationic slow set emulsion	0.8-1.5%	pH 2-7 hydrochloric acid
----------------------------	----------	-----------------------------

No acid is required to prepare stable emulsions

### Specification

Activity, %	48-52	PM 5.020
pH (10% in water)	6-9	EP 5003N

### Physical properties

Appearance at 25°C (77°F)	liquid			
Flash point, °C	24 (75°F)			
Pour point, °C	-21 (-6°F)			

	10	20	30	40	°C
	50	68	86	104	°F
Density, g/cc	0.95	0.94	0.93	0.92	
Density, lbs/U.S. gal	7.93	7.84	7.76	7.68	
Viscosity, mPa.s (cP)	45	31	26	24	

Physical properties are typical data based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

## Packaging information

Redicote E-11 E is available in bulk shipment, in tight head lined steel drums of 415 lbs (188 kg) net weight, or in one-way totes (IBCs) of 2000 lbs (907 kg) net weight.

## Notes

A version of this product with high flash point is available as Redicote E-11 HF-1.

Contact us directly for detailed product information and sample request  
website | [nouryon.com/markets/asphalt](https://nouryon.com/markets/asphalt)  
email | [asphalt@nouryon.com](mailto:asphalt@nouryon.com)

# Nouryon

Nouryon is a global, specialty chemicals leader. Markets and consumers worldwide rely on our essential solutions to manufacture everyday products, such as personal care, cleaning goods, paints and coatings, agriculture and food, pharmaceuticals, and building products. Furthermore, the dedication of more than 7,900 employees with a shared commitment to our customers, business growth, safety, sustainability and innovation has resulted in a consistently strong financial performance. We operate in over 80 countries around the world with a portfolio of industry-leading brands. Visit our website and follow us @Nouryon and on LinkedIn.

All information concerning our products and/or all suggestions for handling and use contained herein (including formulation and toxicity information) are offered in good faith and are believed to be reliable. However, Nouryon makes no warranty express or implied (i) as to the accuracy or sufficiency of such information and/or suggestions, (ii) as to any product's merchantability or fitness for a particular use or (iii) that any suggested use (including use in any formulation) will not infringe any patent. Nothing contained herein shall be construed as granting or extending any license under any patent. The user must determine for itself by preliminary tests or otherwise the suitability of any product and of any information contained herein (including but not limited to formulation and toxicity information) for the user's purpose. The safety of any formulations described herein has not been established. The suitability and safety of a formulation should be confirmed in all respects by the user prior to use. The information contained herein supersedes all previously issued bulletins on the subject matter covered.

Products mentioned are trademarks of Nouryon and registered in many countries.

[nouryon.com](https://nouryon.com)