



Redicote® E-16

Liquid emulsifier for cationic rapid- and medium-setting bitumen emulsions suitable for chip seal, tack coat and open graded cold mix. Active adhesion promoter for pre-coated chips, cutback or soft bitumen

Benefits and features

- Low use level**
 0.15-0.22% is normally sufficient for rapid-set emulsions
- Medium emulsion viscosity**
 Redicote E-16 produces high residue cationic rapidsetting emulsions with moderate viscosity build, suitable for most bitumen types
- Easy handling and storage**
 Redicote E-16 is a low viscosity liquid, easily soluble in the kerosene used in pre-coated chippings, and easily dissolved during the preparation of emulsion soap phase
- Active adhesion**
 Bitumen treated with Redicote E-16 has the ability to displace water from the surface of aggregates

Storage and handling

Redicote E-16 may be stored in carbon steel tanks. Bulk storage should be maintained at 25-35°C (77-95°F). Avoid extended heating above 65°C (150°F). Redicote E-16 contains amines and is corrosive to skin and eyes. Protective goggles and gloves must be worn when handling this product. For further information consult the Safety Data Sheet.

Packaging information

Europe: Redicote E-16 is available in bulk shipment, in tight head steel drums of 170 kg (375 lbs) net weight or in one-way totes (IBCs) of 800 kg (1763 lbs) net weight.

USA: Redicote E-16 is available in bulk shipment, or in tight head steel drums of 360 lbs (163 kg) net weight.

Dosage

Cationic rapid set emulsion	0.15-0.22%	pH 2-4.5 hydrochloric acid
Cationic medium set emulsion	0.25-0.50%	pH 1-4.5 hydrochloric acid
Pre-coated chips	0.1 kg/t	basis aggregate
Cutback bitumen	0.5-1.2%	basis binder

Specification

Amine value, meq/g	min 5.5	VV 1.001
Iodine value, $gl_2/100\text{ g } \%$	>60	VV 1.002
Water, %	max 2	VE 4.003

Physical properties

Appearance at 25°C (77°F)	liquid
Flash point, °C	188 (>370°F)
Pour point, °C	15 (59°F)

	20	30	40	°C
	68	86	104	°F
Density, g/cc	0.84	0.84	0.83	
Density, lbs/U.S. gal	7.02	7.00	6.93	
Viscosity, mPa.s (cP)	42	17	12	

Physical properties are typical data based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

Contact us directly for detailed product information and sample request
website | nouryon.com/markets/asphalt
email | asphalt@nouryon.com

Nouryon

Nouryon is a global, specialty chemicals leader. Markets and consumers worldwide rely on our essential solutions to manufacture everyday products, such as personal care, cleaning goods, paints and coatings, agriculture and food, pharmaceuticals, and building products. Furthermore, the dedication of more than 7,900 employees with a shared commitment to our customers, business growth, safety, sustainability and innovation has resulted in a consistently strong financial performance. We operate in over 80 countries around the world with a portfolio of industry-leading brands. Visit our website and follow us @Nouryon and on LinkedIn.

All information concerning our products and/or all suggestions for handling and use contained herein (including formulation and toxicity information) are offered in good faith and are believed to be reliable. However, Nouryon makes no warranty express or implied (i) as to the accuracy or sufficiency of such information and/or suggestions, (ii) as to any product's merchantability or fitness for a particular use or (iii) that any suggested use (including use in any formulation) will not infringe any patent. Nothing contained herein shall be construed as granting or extending any license under any patent. The user must determine for itself by preliminary tests or otherwise the suitability of any product and of any information contained herein (including but not limited to formulation and toxicity information) for the user's purpose. The safety of any formulations described herein has not been established. The suitability and safety of a formulation should be confirmed in all respects by the user prior to use. The information contained herein supersedes all previously issued bulletins on the subject matter covered.

Products mentioned are trademarks of Nouryon and registered in many countries.

nouryon.com