



Redicote® EM-44A

Emulsifier for cationic rapid and medium setting bitumen emulsions suitable for chip seal, tack coat and open-graded cold mix. Emulsifier for slurry surfacing and cold mix when used with phosphoric acid.

Benefits and features

- Easy dispersion**
 The product is fully liquid, disperses very easily in water and is particularly suitable for in-line plants. Soap concentrates containing up to 20% active material can be prepared.
- Good adhesion**
 The product provides emulsions with excellent storage and pumping stability
- Low emulsion viscosity**
 Emulsions produced with Redicote EM-44A have relatively low viscosity, which can be an advantage when dealing with problematic viscosity-building bitumens
- Phosphoric acid systems**
 Redicote EM-44A can be used with phosphoric acid to produce emulsions suitable for micro surfacing or cold mix

Storage and handling

Redicote EM-44A may be stored in carbon steel tanks. Bulk storage should be maintained at 15-30°C (59-86°F). Redicote EM-44A contains amines and may cause severe irritation or burns to skin and eyes. Protective goggles and gloves must be worn when handling this product. For further information consult the Safety Data Sheet.

Packaging information

Redicote EM-44A is available in bulk shipment, in tight head steel drums of 360 lbs (163 kg) net weight, or in one-way totes (IBCs) of 2100 lbs (953 kg) net weight.

Dosage

Cationic rapid set emulsion	0.18-0.25%	pH 1.5-3.0 hydrochloric acid
Cationic medium set emulsion	0.25-0.50%	pH 1.5-3.0 hydrochloric acid
Micro surfacing	0.9-2.0%	pH 2-3 phosphoric acid

Specification

Amine value, mg KOH/g	200-230	VE 5.007
Water, %	max 1	VE 5.022

Physical properties

Appearance at 25°C (77°F)	liquid
Flash point, °C	>100 (>212°F)
Pour point, °C	10 (50°F)

	20	30	40	50	°C
	68	86	104	122	°F
Density, g/cc	0.87	0.86	0.85	0.85	
Density, lbs/U.S. gal	7.24	7.18	7.14	7.11	
Viscosity, mPa.s (cP)	1000	600	350	250	

Physical properties are typical data based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

Contact us directly for detailed product information and sample request
website | nouryon.com/markets/asphalt
email | asphalt@nouryon.com

Nouryon

Nouryon is a global, specialty chemicals leader. Markets and consumers worldwide rely on our essential solutions to manufacture everyday products, such as personal care, cleaning goods, paints and coatings, agriculture and food, pharmaceuticals, and building products. Furthermore, the dedication of more than 7,900 employees with a shared commitment to our customers, business growth, safety, sustainability and innovation has resulted in a consistently strong financial performance. We operate in over 80 countries around the world with a portfolio of industry-leading brands. Visit our website and follow us @Nouryon and on LinkedIn.

All information concerning our products and/or all suggestions for handling and use contained herein (including formulation and toxicity information) are offered in good faith and are believed to be reliable. However, Nouryon makes no warranty express or implied (i) as to the accuracy or sufficiency of such information and/or suggestions, (ii) as to any product's merchantability or fitness for a particular use or (iii) that any suggested use (including use in any formulation) will not infringe any patent. Nothing contained herein shall be construed as granting or extending any license under any patent. The user must determine for itself by preliminary tests or otherwise the suitability of any product and of any information contained herein (including but not limited to formulation and toxicity information) for the user's purpose. The safety of any formulations described herein has not been established. The suitability and safety of a formulation should be confirmed in all respects by the user prior to use. The information contained herein supersedes all previously issued bulletins on the subject matter covered.

Products mentioned are trademarks of Nouryon and registered in many countries.

nouryon.com