

# Rediset® LQ-900

Compaction aid for hot and warm mixes. Allows a reduction in mixing and paving temperatures while providing active and passive adhesion.

#### Benefits and features

#### Active and passive adhesion

Rediset LQ-900 enables treated bitumen to actively coat damp aggregate which ensures good coverage even at lower mixing temperatures. It also provides long term adhesion which improves durability and lifetime of the asphalt pavement.

#### Cost effective

Rediset LQ-900 is a lower cost yet 100% active product

#### • Improved workability and compaction

Mixes remain workable to lower temperatures and are easier to compact which enables cool weather paving, longer haul distances and faster paving operations

# Heat stability

Performance is maintained after 3-5 days storage in hot bitumen

#### • Easy to use

The product has lower viscosity at ambient temperatures compared to other products

#### Storage and handling

Rediset LQ-900 may be stored in carbon steel tanks. Bulk storage should be maintained at 10-40°C (50-105°F). Avoid heating above 65°C (150°F). Rediset LQ-900 contains amines and may cause severe irritation or burns to skin and eyes. Protective gloves and safety goggles must be used when handling this product.

For further information consult the Safety Data Sheet.

### Dosage

Hot and warm mix	0.5-0.7%	basis binder
Compactability aid	0.3-0.5%	basis binder
Adhesion promoter	0.3-0.5%	basis binder

# **Specification**

Acid value, mg KOH/g	<10	VE 2.013
Amine value, mg HCl/g	265-290	VE 2.018

# Physical properties

7 1 1							
Appearance at 25°C (77°F)	)	amber liquid					
Flash point, °C		>2	.00				
Pour point, °C		3					
	10		20	30	40	$^{\circ}C$	
	50	1	68	86	104	°F	
Density, g/cc			0.926			_	
Viscosity, mPa.s (cP)	209	9	117	44		_	

Physical properties are typical data based on our own measurements or derived from the literature. They do not constitute part of the delivery specification.

# Packaging information

Rediset LQ-900 is available in bulk shipments, in tight head drums of 190 kg (419 lb) net weight, or in one-way totes (IBCs) of 900 kg (1984 lbs).

# Notes

For more information see the Technical Bulletin: Rediset LQ.

Contact us directly for detailed product information and sample request website | nouryon.com/markets/asphalt email | asphalt@nouryon.com

# Nouryon

Nouryon is a global, specialty chemicals leader. Markets and consumers worldwide rely on our essential solutions to manufacture everyday products, such as personal care, cleaning goods, paints and coatings, agriculture and food, pharmaceuticals, and building products. Furthermore, the dedication of more than 7,900 employees with a shared commitment to our customers, business growth, safety, sustainability and innovation has resulted in a consistently strong financial performance. We operate in over 80 countries around the world with a portfolio of industry-leading brands. Visit our website and follow us @Nouryon and on LinkedIn.

All information concerning our products and/or all suggestions for handling and use contained herein (including formulation and toxicity information) are offered in good faith and are believed to be reliable. However, Nouryon makes no warranty express or implied (i) as to the accuracy or sufficiency of such information and/or suggestions, (ii) as to any product's merchantability or fitness for a particular use or (iii) that any suggested use (including use in any formulation) will not infringe any patent. Nothing contained herein shall be construed as granting or extending any license under any patent. The user must determine for itself by preliminary tests or otherwise the suitability of any product and of any information contained herein (including but not limited to formulation and toxicity information) for the user's purpose. The safety of any formulations described herein has not been established. The suitability and safety of a formulation should be confirmed in all respects by the user prior to use. The information contained herein supersedes all previously

Products mentioned are trademarks of Nouryon and registered in many countries.

nouryon.com